

Extrusion profiles

Overview of the alloys:

Alloy, Brand name	Tensile strength	elastic limit	Elongation at break	Hardness value
6060 T6 Extrudal-043	215	160	8	70
6063 T6 Extrudal-050	215	170	12	70
6082 T6 Anticorodal-100	310	260	8	100